

SPECIFICATION PRODUCT CODE - 110 - KRAFT

PRODUCT CODE	GSM	BF	RCT Kn/m (MD-CD)	TF (MD-CD)	COBB (60 sec)	Moisture %
11018	120	18	NA	45-50	45 \pm 5	6.5-7.0
	140	18	NA	50-55	45 \pm 5	6.5-7.0
	150	18	NA	55-60	45 \pm 5	6.5-7.0
	180	18	NA	60-65	45 \pm 5	6.5-7.0
	200	18	NA	65-70	45 \pm 5	6.5-7.0
	220	18	NA	75-80	45 \pm 5	6.5-7.0
	250	18	NA	80-88	45 \pm 5	6.5-7.0
11020	120	20	NA	55-62	45 \pm 5	6.5-7.0
	140	20	1.2-1.0	60-68	45 \pm 5	6.5-7.0
	150	20	1.3-1.1	60-70	45 \pm 5	6.5-7.0
	180	20	1.9-1.5	70-78	45 \pm 5	6.5-7.0
	200	20	2.3-1.7	78-86	45 \pm 5	6.5-7.0
	220	20	2.5-1.9	88-98	45 \pm 5	6.5-7.0
	250	20	2.6-2.0	90-100	45 \pm 5	6.5-7.0
11022	120	22	NA	58-65	45 \pm 5	6.5-7.0
	140	22	1.25-1.05	62-70	45 \pm 5	6.5-7.0
	150	22	1.45-1.15	62-70	45 \pm 5	6.5-7.0
	180	22	2.3-1.7	72-80	45 \pm 5	6.5-7.0
	200	22	2.5-1.9	82-90	45 \pm 5	6.5-7.0
	220	22	2.6-2.0	92-100	45 \pm 5	6.5-7.0
	250	22	2.8-2.25	94-104	45 \pm 5	6.5-7.0
11024	120	24	NA	60-68	45 \pm 5	6.5-7.0
	140	24	1.35-1.1	63-73	45 \pm 5	6.5-7.0
	150	24	1.5-1.2	65-75	45 \pm 5	6.5-7.0
	180	24	2.6-1.8	75-85	45 \pm 5	6.5-7.0
	200	24	2.8-2.0	84-92	45 \pm 5	6.5-7.0
	220	24	3.0-2.2	94-108	45 \pm 5	6.5-7.0
	250	24	3.3-2.5	96-110	45 \pm 5	6.5-7.0
11028	120	28	NA	60-80	45 \pm 5	6.5-7.0
	140	28	1.45-1.2	63-73	45 \pm 5	6.5-7.0
	150	28	1.6-1.35	65-75	45 \pm 5	6.5-7.0
	180	28	2.6-1.95	68-78	45 \pm 5	6.5-7.0
	200	28	2.8-2.1	88-98	45 \pm 5	6.5-7.0
	220	28	3.1-2.3	95-110	45 \pm 5	6.5-7.0
	250	28	3.5-2.6	98-115	45 \pm 5	6.5-7.0
11035	120	35	NA	65-75	45 \pm 5	6.5-7.0
	140	35	2.1-1.5	68-78	45 \pm 5	6.5-7.0
	150	35	2.2-1.6	72-82	45 \pm 5	6.5-7.0
	180	35	3.1-2.1	85-95	45 \pm 5	6.5-7.0
	200	35	3.5-2.25	95-110	45 \pm 5	6.5-7.0
	220	35	3.7-2.5	105-115	45 \pm 5	6.5-7.0
	250	35	4.0-2.8	108-120	45 \pm 5	6.5-7.0

Contact Us:
Ph: +91 9999535321, +91 9717538855 | **Email:** Export@knammarketing.com | **Website:** www.knammarketing.com